

FORM PCT 1390
REV. 5/93

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NO.
BRODESSER ET AL. - 1 (PCT)

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

U.S. APPLICATION NO. (if known, see 37 CFR 1.5)

09/937202

INTERNATIONAL APPLICATION NO.
PCT/DE00/00883

INTERNATIONAL FILING DATE
24 MARCH 2000

PRIORITY DATE CLAIMED
25 MARCH 1999

TITLE OF INVENTION

METHOD FOR LINKING TWO PLASTIC COMPONENTS

APPLICANT(S) FOR DO/EO/US

KAY BRODESSER ET AL.

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:



1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371 (f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☒ is transmitted herewith (required only if not transmitted by the International Bureau)
 - b. ☐ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)).
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has **NOT** expired.
 - d. ☐ have not been made and will not be made.
8. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11. to 16. below concern other document(s) or information included:

11. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A **FIRST** preliminary amendment.
☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
14. ☐ A substitute specification.
15. ☐ A change of power of attorney and/or address letter.
16. ☒ Other items or information:

PCT/ISA/210 - Int'l. Search Report (English)
1 Sheet of Formal Drawings

Applicants Claim Priority under 35 U.S.C. §119 of German Application No. 199 13 501.0 filed March 25, 1999.
Applicants Claim Priority under 35 U.S.C. §120 of: PCT/DE00/00883 filed March 24, 2000.

APPLICATION NO. (if known, see 37 CFR 1.5) 09/937202				INTERNATIONAL APPLICATION NO. PCT/DE00/00883		ATTORNEY'S DOCKET NO. BRODESSER ET AL.-1	
<input checked="" type="checkbox"/> The following fees are submitted: Basic National Fee (37 CFR 1.492(a)(1)-(5)): Search Report has been prepared by the EPO or JPO.....\$860.00 International preliminary examination fee paid to USPTO (37 CFR 1.482)\$690.00 Neither international preliminary examination fee paid (37 CFR 1.82) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO.....\$1,000.00 International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(2)-(4).....\$100.00 ENTER APPROPRIATE BASIC FEE AMOUNT =				CALCULATIONS		PTO USE ONLY	
Surcharge of \$130.00 for furnishing the oath or declaration later than ____ 20 ____ 30 months from the earliest claimed priority date (37 CFR 1.492(e)).							
Claims	Number Filed	Number Extra	Rate				
Total Claims	14 - 20 =	- 0 -	X \$18.00	\$			
Independent Claims	1 - 3 =	- 0 -	X \$80.00	\$			
Multiple dependent claim(s) (if applicable)			+ \$270.00	\$			
TOTAL OF ABOVE CALCULATIONS =				\$ 860.00			
Reduction by 1/2 for Small Entity status.				\$			
SUBTOTAL =				\$ 860.00			
Processing fee of \$130.00 for furnishing the English translation later than ____ 20 ____ 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$			
TOTAL NATIONAL FEE =				\$ 860.00			
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +				See cover sheet attached to assign \$ to be charged to Deposit Acct			
TOTAL FEES ENCLOSED =				\$ 860.00			
				Amount to be: refunded		\$	
				charged		\$	
<p>Applicant claims Small Entity status.</p> <p>a. <input checked="" type="checkbox"/> A check in the amount of \$ <u>860.00</u> to cover the above fees is enclosed.</p> <p>b. <input type="checkbox"/> Please charge my Deposit Account No. 03-2468 in the amount of \$ _____ to cover the above fees. A duplicate copy of this sheet is enclosed.</p> <p>c. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment, to Deposit Account No. 03-2468. A duplicate copy of this sheet is enclosed.</p> <p>NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.</p> <div style="display: flex; justify-content: space-between;"> <div style="width: 40%;"> <p>SEND ALL CORRESPONDENCE TO: COLLARD & ROE, P.C. 1077 Northern Boulevard Roslyn, New York 11576-1696 (516) 365-9802</p> </div> <div style="width: 55%; text-align: center;">  Signature <u>Edward R. Freedman</u> <u>Reg. No. 26,048</u> </div> </div> <p>Express Mail No. EL 871 448 045 US Date of Deposit September 21, 2001</p> <p>I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10, on the date indicated above, and is addressed to the Ass't. Commissioner for Patents, Washington, D.C. 20231</p> <div style="text-align: center;">  Lisa L. Vulpis </div>							

PATENTIN THE UNITED STATES PATENT AND TRADEMARK OFFICE

APPLICANTS: KAY BRODESSER ET AL. - 1 (PCT)
PCT NO.: PCT/DE00/00883
FILED: MARCH 24, 2000
TITLE: METHOD FOR LINKING TWO PLASTIC COMPONENTS

PRELIMINARY AMENDMENT**BOX PCT**

Ass't. Commissioner for Patents
Washington, D.C. 20231

Dear Sir:

Preliminary to the initial Office Action, please amend the
above-identified application as follows:

IN THE ABSTRACT:

Please add the attached Abstract of the Disclosure on a
separate page.

IN THE SPECIFICATION:

On Page 1, above line 1, please insert the following
paragraphs:

--CROSS REFERENCE TO RELATED APPLICATIONS

Applicants claim priority under 35 U.S.C. §119 of German
Application No. 199 13 501.0 filed March 25, 1999. Applicants
also claim priority under 35 U.S.C. §120 of PCT/DE00/00883 filed

March 24, 2000. The international application under PCT article 21(2) was not published in English.--

On page 1, please replace the first full paragraph with the following paragraph:

--This invention relates to a method of joining a first component made of plastic to a second component made of plastic having the features according to the definition of the species of Claim 15.--

On page 1, after the third full paragraph, please insert the following new paragraphs:

--U.S. Patent 5,266,262 describes blow-molded intake manifolds onto which a common flange is integrally molded. The intake manifolds have connecting sections which are embedded in the plastic of the flange in integral molding. Ring-shaped projections extending outward are formed on these connecting sections and are anchored like a barb in the integrally molded flange in a form-fitting manner. The strength, in particular the tensile strength, of this connection is increased in this way.

U.S. Patent 4,752,208 describes a method which is used for integral molding of a coupling sleeve onto a corrugated tube hose. The injection mold and the injection process are

coordinated so that at least two corrugations on the end of the corrugated tube to be sheathed are compressed, with the one corrugation sealing the injection mold while the other corrugation is embedded as an anchor in the integrally molded sheathing. In addition, the parameters are selected in this process so that the sheathed corrugated tube end softens, fuses at the surface and forms a bond with the integrally molded sheathing. However, the sheathed corrugated tube end and the compressed corrugations are retained as such.--

On page 3, please replace the first full paragraph with the following paragraph:

--This problem is solved according to this invention by a method having the features of Claim 15.--

A marked-up version of the prior pending paragraphs is attached as Exhibit A.

IN THE CLAIMS:

Please cancel claims 1-14 and replace them with new claims 15-28 as follows:

--15. A method of joining a first component (6) made of plastic to a second component (9) made of plastic, where the first component (6) is introduced into an injection mold with at

least a connecting section where the connection to the second component (9) is to be formed, the second component (9) being produced by integral molding of plastic onto the connecting section (12) of the first component (6), one surface (13) of the connecting section (12) being wetted at least partially by the plastic of the second component (9),

characterized in that

at least one bonding body (14) is formed on the surface (13) of the connecting section (12) which is provided for wetting by the plastic of the second component (9), said bonding body being fixedly connected to it and designed so that it melts in integral molding of the plastic of the second component (9) due to the thermal energy of the integrally molded plastic and it melts with the integrally molded plastic, whereupon the bonding body (14) is at least partially subsumed into the integrally molded plastic and becomes integrated into the integrally molded component (9).

16. The method according to Claim 15,

characterized in that

each bonding body (14) is formed by an elevation which projects away from the surface (13) of the connecting section (12) and is integrally molded onto the first component (6) in the manufacture of the latter, so that each bonding body (14) is produced in one piece with the connecting section (12).

17. The method according to Claim 16,
characterized in that
each elevation (14) tapers with increasing distance
from the surface (13).

18. The method according to Claim 16,
characterized in that
the elevations (14) run along the surface (13) in the
form of a ring, in particular a circular ring, in the case of a
cylindrical first component (6), in particular a round
cylindrical component.

19. The method according to Claim 15,
characterized in that
the temperature at which the plastic of the second
component (9) is injected into the injection mold (injection
temperature) is close to the upper limit of a temperature range
in which the injection molding method can be carried out with
this plastic.

20. The method according to Claim 15,
characterized in that
the pressure at which the plastic of the second
component (9) is injected into the injection mold (injection
pressure) is close to the upper limit of a pressure range in

which the injection molding process can be carried out with this plastic.

21. The method according to Claim 15,
characterized in that
the plastic of the first component (6) has a high
viscosity relative to that of the integrally molded plastic of
the second component (9).

22. The method according to Claim 15,
characterized in that
the first component (6) is designed as a blow-molded
part, i.e., as a component produced by a blow-molding method.

23. The method according to Claim 15,
characterized in that
the respective melting points of the plastics of the
two component (6, 9) are in approximately the same range.

24. The method according to Claim 15,
characterized in that
the plastics of the two components (6, 9) each have
only a relatively narrow temperature range for processing their
melts.

25. The method according to Claim 15,
characterized in that

the components (6, 9) are each made of a polyamide plastic.

26. The method according to Claim 15,
characterized in that

the components (6, 9) are each made of a fiber-reinforced plastic, in particular a fiberglass-reinforced or carbon fiber-reinforced polyamide plastic.

27. The method according to Claim 15,
characterized in that

the first component is an intake manifold (6) of an intake manifold system (1) which receives the air from an air supply which is provided for combustion in the internal combustion engine and distributes it to individual combustion chambers of the internal combustion engine, and the second component is a flange (9) of the intake manifold system (1) which can be connected to the internal combustion engine.

28. The method according to Claim 27,
characterized in that


the intake manifold system (1) has a modular design, with an air distributor module (2) made of plastic which can be connected to the air supply of the internal combustion engine, with several intake manifold modules (6), each made of plastic and designed in one piece, connected at their one pipe end (7) to the air distributor module (2) and each assigned to one of the

combustion chambers of the internal combustion engine, and with at least one flange module (9) made of plastic in one piece to which at least one of the intake manifold modules (6) is connected at its other pipe end (8).--

REMARKS

By this Preliminary Amendment, the application has been amended to conform with U.S. practice, the cross-reference to related applications has been inserted on page 1, the specification has been amended to change claim dependencies, claims 1-14 have been canceled and replaced with new claims 15-28 and an Abstract has been provided. No new matter has been introduced. Entry of this amendment is respectfully requested.

Respectfully submitted,
KAY BRODESSER ET AL. - 1 (PCT)


Allison C. Collard, Reg.No. 22,532
Edward R. Freedman, Reg.No. 26,048
Attorneys for Applicants

COLLARD & ROE, P.C.
1077 Northern Boulevard
Roslyn, New York 11576
(516) 365-9802


erf:jc

Enclosure: Abstract
Exhibit A

Express Mail No. EL 871 448 045 US

Date of Deposit September 21, 2001

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 C.F.R. § 1.10, on the date indicated above, and is addressed to the Ass't. Commissioner for Patents, Washington, D.C. 20231


Lisa L. Vulpis

ABSTRACT OF THE DISCLOSURE

The invention relates to a method for linking a first plastic component (6) with a second plastic component (9). According to the inventive method, the first component (6) is introduced into an injection mold with at least one connecting section (12) at which the link with the second component (9) is to be established. The second component (9) is formed by injection-molding plastic material onto the connecting section. A surface of the connecting section (12) is at least partially covered by the plastic material of the second component (9). At least one of the components may consist of a plastic material that requires only a relatively narrow temperature range to be moldable in the molten state. At least one binder body is formed at the surface intended to be covered by the injection-molded plastic material which binder is firmly linked with the surface. Said binder melts when contacted with the heat energy of the injection-molded plastic material and fuses with the injection-molded plastic.

EXHIBIT A

Marked-up Version of Prior Pending
Paragraphs Showing the Changes Made

On page 1, please replace the first full paragraph with the following paragraph:

--This invention relates to a method of joining a first component made of plastic to a second component made of plastic having the features according to the definition of the species of Claim [1] 15.--

On page 3, please replace the first full paragraph with the following paragraph:

--This problem is solved according to this invention by a method having the features of Claim [1] 15.--

METHOD OF LINKING TWO PLASTIC COMPONENTS

This invention relates to a method of joining a first component made of plastic to a second component made of plastic having the features according to the definition of the species of Claim 1.

Such a method is known from European Patent 0 567 702 B1, for example. To connect a first plastic component, such as an intake manifold of an intake manifold system of an internal combustion engine to a second plastic component such as a flange of this intake manifold system, the first component having at least one connecting section on which the connection to the second component is to be created is introduced into an injection mold. The second component is then formed by integral molding of plastic onto the connecting section of the first component, whereby one surface of the connecting section is at least partially wetted by plastic of the second component.

Through appropriate shaping of the connecting section, in particular through an increasing wall thickness and a suitable embedding of the connecting section in the plastic material of the integrally molded component, where the integrally molded component largely encompasses or surrounds the connecting section of the other component, a form-fitting connection that can withstand relatively high static stresses can be established between the components.

In order for such a connection to have a long lifetime even under high-frequency dynamic stresses and to be able to guarantee that the connection will be leakproof even at high pressures during this lifetime, the components must be bonded together. To this end, the first component onto which the second component is to be integrally molded may be heated before being inserted into the injection mold so that the plastic softens or begins to fuse in the area of

the connecting section. In this condition, the first component can then be inserted into the injection mold. Then the molding operation is performed, with the molten injected plastic and the partially fused plastic at the surface of the first component being fused together. The desired intimate bonding connection is formed on solidification of the melts which have thus been mixed in this way. The plastics to be joined by bonding in this way are preferably compatible and are based on the same basic substance.

However, such a method cannot be used when at least one of the components is made of a plastic which has a relatively small or narrow temperature range for processability of the melt thereof. In other words, there is only a relatively short distance between a minimum melt temperature, which is the minimum necessary for processing of the melt, and a maximum melt temperature above which it is no longer possible to process the melt as intended. This is the case with polyamide [nylon] plastics, for example. For example, if the first component is made of such a plastic, then the melt on the connecting section which is formed by heating will have cooled again by the start of the injection molding operation to the extent that the desired bonded connection cannot be achieved consistently. In addition, it is relatively complicated to heat or partially fuse the first component and transfer it to the injection mold. If, in contrast with this, the component to be integrally molded is made of a plastic of the above-mentioned type, the melt compound will rapidly cool to a temperature below the aforementioned minimum melt temperature as soon as the melt compound comes in contact with the first plastic component in the integral molding operation.

The present invention relates to the problem of designing a method of the type defined in the preamble such that a bonded connection can be established relatively

inexpensively between two plastic components even if the plastic of one component and/or the other has a relatively narrow temperature range for processability of its melt.

This problem is solved according to this invention by a method having the features of Claim 1.

This invention is based on the general idea of orienting the thermal energy transferred from the integrally molded plastic to the first component through the design of bonding bodies at the surface of the connecting section of the first component in such a way that these bonding bodies thus melt and can fuse with the integrally molded plastic. Thus, due to this controlled thermal conduction, preferred melting zones are formed on the connecting section where surface melting takes place rapidly enough to form the desired high-quality bonded connection of the two components.

According to a preferred embodiment, the bonding bodies may be formed by elevations that are formed on the component at the time of its manufacture and project away from the surface of the connecting section, so that the bonding bodies are formed in one piece with the connecting section. Due to the fact that the bonding bodies are taken into account in the production and design of the first component, there is no increase in cost for production of the first component. In addition, due to their integration into the shape of the first component, these bonding bodies are connected to it in a highly effective manner. Since the bonding bodies project away from the surface of the connecting section, the heat transferred to the integrally molded plastic on coming in contact with the latter cannot be dissipated rapidly enough over the connecting section or the first component, so there is a buildup of heat with the desired result that the plastic of the first component melts at the surface in the area of the connecting section

at the bonding bodies, permitting fusion with the integrally molded plastic.

With the method proposed according to this invention, it is also possible to integrally mold a component which, as an injection molded part, consists of a plastic which has a low viscosity in the melt, onto a component made of a plastic which has a high viscosity in the melt. The highly viscous plastic on the bonding bodies is heated and liquefied to the extent that it can mix or bond with the low-viscosity integrally molded plastic. In particular, it is thus possible to design the first component as a blow-molded part, in other words, the first component is produced by a blow-molding method. In order for this to be possible, the first component must be made of a high-viscosity plastic.

To improve the surface melting of the bonding bodies, the temperature at which the plastic of the second component is injected into the injection mold, i.e., the injection temperature, is selected so as to be close to the upper limit of the temperature range in which an injection molding method can be carried out with this plastic. This measure increases the amount of heat that can be transferred from the injected plastic to the first component.

Additional important features and advantages of the method according to this invention are derived from the subordinate claims, the drawings and the respective description of the figures on the basis of the drawings.

It is self-evident that the features mentioned above and to be explained below can be used not only in the combination described here but also in any other combinations or alone without going beyond the scope of the present invention.

A preferred embodiment of this invention is illustrated in the drawings and is explained in greater detail in the following description.

Figure 1: shows a schematic sectional view through an intake manifold system of an internal combustion engine manufactured using the method according to this invention, and

Figure 2: shows an enlarged detail of a section labeled as II in Figure 1.

According to Figure 1, a modular intake manifold system 1, which distributes to individual combustion chambers of an internal combustion engine (not shown) the air supplied by an air intake for combustion in the internal combustion engine, has an air distributor module 2 which has a modular design itself and is composed of an upper one-piece air distributor top part module 3 and a lower one-piece air distributor bottom part module 4. The air distributor modules 3 and 4 each have a collar or shoulder 5 that projects outward and runs completely around the circumference, where the two modules 3 and 4 can be joined together, in particular by a friction welding method.

Several one-piece intake manifold modules 6 are connected or attached to the top side of the air distributor top part module 3, but only one is illustrated in Figure 1, because the components of the intake manifold system 1 arranged behind the plane of the drawing in the direction of view have been omitted for the sake of simplifying the diagram. The intake manifold module 6 is connected at one end at a pipe end 7 to the air distributor module 2 and at the other end at a pipe end 8 to a flange module 9 which can be connected to the internal combustion engine. Thus, the air introduced into the air distributor module 2 through the intake manifold module 6 can reach the respective combustion chamber of the internal combustion engine.

A receptacle 10 is provided in the flange module 9 so that an injection valve 11 can be mounted in the receptacle, as indicated in Figure 1.

The intake manifold system is manufactured as follows:

First the intake manifold modules 6 are produced, preferably with the help of a blow-molding method, so the shape of the intake manifold modules 6 can be varied relatively easily; for example, the pipe diameter, the radius of curvature and the pipe length can be adapted in this way to the different configurations of the internal combustion engine. The intake manifold modules 6, each assigned to one flange module 9, are then inserted into an injection mold, at least at their pipe ends 8. Then an injection molding process can be carried out to form the flange module 9. The pipe end 8 assigned to the flange 8 is designed so that it is encompassed by the plastic of the flange module 9 on both sides, i.e., on the inside and outside with respect to the intake manifold module 6. In addition, the wall thickness of the intake manifold module 6 increases in this pipe end 8, so that a highly effective anchoring of the intake manifold module 6 in the flange module 9 is produced on the whole. Thus, the pipe end 8 is joined in a form-fitting manner to the flange module 9. The method according to this invention is also used to form a high-quality, strong and tight bonded connection between the intake manifold module 6 and the flange module 9.

To this end, bonding bodies 14 are formed at least on an exterior surface 13 on a connecting section 12 of the pipe end 8 where the connection to the flange 9 is formed. These bonding bodies 14 here are in the form of elevations running in a ring around the circumference, projecting outward away from the surface 13 and tapering to a tip. The dimensions of these elevations are small relative to the

dimensions of the components 6, 9 which are to be joined together. For example, the elevations 14 may project 1 mm away from the surface 13. The bonding bodies 14 are designed in one piece with the connecting section 12, i.e., they are unmolded together with it in the manufacture of the intake manifold module 6. In integral molding of the plastic to form the flange module 9, the selected geometry of the bonding bodies 14 causes the thermal energy transmitted in them from the integrally molded plastic to the connecting section 12 to collect and cause the bonding bodies 14 to begin to melt. In this way, the melts can become mixed together, so that the two components 6 and 9 become fused together in the area of their bonding. The desired form-fitting bonding which is strong and tight is formed between the components 6 and 9 on solidification of this combined melt of the two components in the area of the joint.

After carrying out the method according to this invention, the pipe ends 7 of the intake manifold modules 6 facing away from the flange module 9 are joined to the air distributor module 2 as illustrated in Figure 1, for which purpose the connection of the intake manifold module 6 to the air distributor module 2 is designed as a plug connection here. The pipe end 7 forms an external connection while the air distributor top part module 3 forms an internal connection 15. Connections 7 and 15 may be joined together in the traditional manner, e.g., by a welded joint, a shrink-fit joint, an adhesive bond or by a combination of different joining methods. Then the air distributor bottom part module 4 is integrally molded onto the air distributor top part module 3 by a friction welding method, for example.

Figure 2 shows a part of the pipe end 8 before integral molding of the second component 9, i.e., at a time when the elevations or the bonding bodies 14 have not yet been

deformed by the integral molding process or fused to the integrally molded plastic. Due to the method according to this invention, the bonding bodies 14 at least partially enter the melt or the injection molding compound and are thus integrated into the injection molded part 9.

CLAIMS

1. A method of joining a first component (6) made of plastic to a second component (9) made of plastic, where the first component (6) is introduced into an injection mold with at least a connecting section where the connection to the second component (9) is to be formed,
the second component (9) being produced by integral molding of plastic onto the connecting section (12) of the first component (6),
one surface (13) of the connecting section (12) being wetted at least partially by the plastic of the second component (9),
characterized in that
at least one bonding body (14) is formed on the surface (13) of the connecting section (12) which is provided for wetting by the plastic of the second component (9), said bonding body being fixedly connected to it, melting in integral molding of the plastic of the second component (9) due to the thermal energy of the integrally molded plastic and thus fusing to the integrally molded plastic.
2. The method according to Claim 1,
characterized in that
each bonding body (14) is formed by an elevation which projects away from the surface (13) of the connecting section (12) and is integrally molded onto the first component (6) in the manufacture of the latter, so that each bonding body (14) is produced in one piece with the connecting section (12).
3. The method according to Claim 2,
characterized in that
each elevation (14) tapers with increasing distance from the surface (13).

4. The method according to Claim 2 or 3,
characterized in that
the elevations (14) run along the surface (13) in the form of a ring, in particular a circular ring, in the case of a cylindrical first component (6), in particular a round cylindrical component.
5. The method according to one of Claims 1 through 4,
characterized in that
the temperature at which the plastic of the second component (9) is injected into the injection mold (injection temperature) is close to the upper limit of a temperature range in which the injection molding method can be carried out with this plastic.
6. The method according to one of Claims 1 through 5,
characterized in that
the pressure at which the plastic of the second component (9) is injected into the injection mold (injection pressure) is close to the upper limit of a pressure range in which the injection molding process can be carried out with this plastic.
7. The method according to one of Claims 1 through 6,
characterized in that
the plastic of the first component (6) has a high viscosity relative to that of the integrally molded plastic of the second component (9).
8. The method according to one of Claims 1 through 7,
characterized in that
the first component (6) is designed as a blow-molded part, i.e., as a component produced by a blow-molding method.
9. The method according to one of Claims 1 through 8,

characterized in that

the respective melting points of the plastics of the two component (6, 9) are in approximately the same range.

10. The method according to one of Claims 1 through 9,
characterized in that
the plastics of the two components (6, 9) each have only a relatively narrow temperature range for processing their melts.
11. The method according to one of Claims 1 through 10,
characterized in that
the components (6, 9) are each made of a polyamide plastic.
12. The method according to one of Claims 1 through 11,
characterized in that
the components (6, 9) are each made of a fiber-reinforced plastic, in particular a fiberglass-reinforced or carbon fiber-reinforced polyamide plastic.
13. The method according to one of Claims 1 through 12,
characterized in that
the first component is an intake manifold (6) of an intake manifold system (1) which receives the air from an air supply which is provided for combustion in the internal combustion engine and distributes it to individual combustion chambers of the internal combustion engine, and the second component is a flange (9) of the intake manifold system (1) which can be connected to the internal combustion engine.
14. The method according to Claim 13,
characterized in that
the intake manifold system (1) has a modular design,

with an air distributor module (2) made of plastic which can be connected to the air supply of the internal combustion engine, with several intake manifold modules (6), each made of plastic and designed in one piece, connected at their one pipe end (7) to the air distributor module (2) and each assigned to one of the combustion chambers of the internal combustion engine, and with at least one flange module (9) made of plastic in one piece to which at least one of the intake manifold modules (6) is connected at its other pipe end (8).

1/1




Fig. 1




Fig. 2

For publication

COMBINED DECLARATION FOR PATENT APPLICATION AND POWER OF ATTORNEY
 (Includes Reference to PCT International Applications)

 ATTORNEY'S DOCKET NUMBER
 BRODESSER ET AL-1 PCT

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

METHOD FOR LINKING TWO PLASTIC COMPONENTS

the specification of which (check only one item below):

☐ is attached hereto.

☐ was filed as United States application

Serial No. _____

on _____,

and was amended

on _____ (if applicable).

☒ was filed as PCT international application

Number PCT/DE00/00883 ✓

on 24 MARCH 2000 ✓

and was amended under PCT Article 19

on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, §1.56(a).

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate or of any PCT international application(s) designating at least one country other than the United States of America listed below and have also identified below any foreign application(s) for patent or inventor's certificate or any PCT international application(s) designating at least one country other than the United States of America filed by me on the same subject matter having a filing date before that of the application(s) of which priority is claimed:

PRIOR FOREIGN/PCT APPLICATION(S) AND ANY PRIORITY CLAIMS UNDER 35 U.S.C. 119:

COUNTRY (if PCT, indicate "PCT")	APPLICATION NUMBER	DATE OF FILING (day, month year)	PRIORITY CLAIMED UNDER 35 U.S.C. 119
GERMANY ✓	199 13 501.0 ✓	25 MARCH 1999 ✓	<input checked="" type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO

COMBINED DECLARATION FOR PATENT APPLICATION AND POWER OF ATTORNEY (Includes Reference to PCT International Applications)				ATTORNEY'S DOCKET NUMBER BRODESSER ET AL-1 PCT	
I hereby claim the benefit under Title 35, United States Code, Section 119(e) of any United States provisional application(s) listed below.					
(Application Number)		(Filing Date)			
I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) or PCT international application(s) designating the United States of America that were listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in that/those prior application(s) in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, §1.56(a) which occurred between the filing date of the prior application(s) and the national or PCT international filing date of this application.					
PRIOR U.S. APPLICATIONS OR PCT INTERNATIONAL APPLICATIONS DESIGNATING THE U.S. FOR BENEFIT UNDER 35 U.S.C. 120:					
U.S. APPLICATIONS			STATUS (Check One)		
U.S. APPLICATION NUMBER	U.S. FILING DATE		PATENTED	PENDING	ABANDONED
PCT APPLICATIONS DESIGNATING THE U.S.					
PCT APPLICATION NO	PCT FILING DATE	U.S. SERIAL NUMBER(S) ASSIGNED (if any)			
POWER OF ATTORNEY. As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith. (List name and registration numbers). <div style="display: flex; justify-content: space-between;"> <div> KURT KELMAN, Registration No. 18,628 ALLISON C. COLLARD, Registration No. 22,532 EDWARD R. FREEDMAN, Registration No. 26,048 ELIZABETH COLLARD RICHTER, Registration No. 35,103 </div> <div> FREDERICK J. DORCHAK, Registration No. 29,298 WILLIAM C. COLLARD, Registration No. 38,411 REINE H. GLANZ, Registration No. 46,728 </div> </div>					
Send Correspondence to: <u>COLLARD & ROE, P.C.</u> <u>1077 Northern Boulevard</u> <u>Roslyn, New York 11576</u>			Customer No. <u>25889</u>		Direct Telephone Calls to (name and telephone number) <u>(516) 365-9802</u>
2	FULL NAME OF INVENTOR	FAMILY NAME <u>BRODESSER</u>	FIRST GIVEN NAME <u>KAY</u>	SECOND GIVEN NAME	
0	RESIDENCE & CITIZENSHIP	CITY <u>RUTESHEIM</u> <i>DEX</i>	STATE OR FOREIGN COUNTRY <u>GERMANY</u>	COUNTRY OF CITIZENSHIP <u>GERMANY</u> ✓	
1	POST OFFICE ADDRESS	POST OFFICE ADDRESS <i>Fontanestr. 15</i> <u>DAIMLERSTRASSE 19</u>	CITY <u>D-71277 RUTESHEIM</u>	STATE & ZIP CODE/COUNTRY <u>GERMANY</u>	
2	FULL NAME OF INVENTOR	FAMILY NAME <u>DRESPLING</u>	FIRST GIVEN NAME <u>HANS</u>	SECOND GIVEN NAME	
0	RESIDENCE & CITIZENSHIP	CITY <u>HEIDENHEIM</u> <i>DEX</i>	STATE OR FOREIGN COUNTRY <u>GERMANY</u>	COUNTRY OF CITIZENSHIP <u>GERMANY</u> ✓	
2	POST OFFICE ADDRESS	POST OFFICE ADDRESS <u>FLAMENWEG 44</u>	CITY <u>D-89522 HEIDENHEIM</u>	STATE & ZIP CODE/COUNTRY <u>GERMANY</u>	
2	FULL NAME OF INVENTOR	FAMILY NAME <u>JENSEN</u>	FIRST GIVEN NAME <u>HANS</u>	SECOND GIVEN NAME	
0	RESIDENCE & CITIZENSHIP	CITY <u>KIRCHHEIM</u>	STATE OR FOREIGN COUNTRY <u>GERMANY</u> <i>DEX</i>	COUNTRY OF CITIZENSHIP <u>GERMANY</u> ✓	
3	POST OFFICE ADDRESS	POST OFFICE ADDRESS <u>HEIMENSTEINSTRASSE 12</u>	CITY <u>D-73237 KIRCHHEIM</u>	STATE & ZIP CODE/COUNTRY <u>GERMANY</u>	
I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.					
SIGNATURE OF INVENTOR 201		SIGNATURE OF INVENTOR 462-204		SIGNATURE OF INVENTOR 203	
<i>Kay Thalesser</i>		<i>Günter Kachler</i>		<i>Kas...</i>	
DATE <u>23.8.01</u>		DATE <u>15.8.01</u>		DATE <u>15.08.01</u>	

4-00	2	FULL NAME OF INVENTOR	FAMILY NAME <u>KACHLER</u>	FIRST GIVEN NAME <u>GÜNTER</u>	SECOND GIVEN NAME
	0	RESIDENCE & CITIZENSHIP	CITY <u>INGERSHEIM</u> <i>DEX</i>	STATE OR FOREIGN COUNTRY <u>GERMANY</u>	COUNTRY OF CITIZENSHIP <u>GERMANY</u> ✓
	4	POST OFFICE ADDRESS	POST OFFICE ADDRESS <u>IM STAFFELRAIN 22</u>	CITY <u>D-74379 INGERSHEIM</u>	STATE & ZIP CODE/COUNTRY <u>GERMANY</u>
5-00		FULL NAME OF INVENTOR	FAMILY NAME <u>SCHNEIDER</u>	FIRST GIVEN NAME <u>HORST</u>	SECOND GIVEN NAME
	0	RESIDENCE & CITIZENSHIP	CITY <u>WAIBLINGEN</u> <i>DEX</i>	STATE OR FOREIGN COUNTRY <u>GERMANY</u>	COUNTRY OF CITIZENSHIP <u>GERMANY</u> ✓
	5	POST OFFICE ADDRESS	POST OFFICE ADDRESS <u>BANGERTSTRASSE 50</u>	CITY <u>D-71336 WAIBLINGEN</u>	STATE & ZIP CODE/COUNTRY <u>GERMANY</u>
6-00		FULL NAME OF INVENTOR	FAMILY NAME <u>STEHLLIG</u>	FIRST GIVEN NAME <u>JÜRGEN</u>	SECOND GIVEN NAME
	0	RESIDENCE & CITIZENSHIP	CITY <u>NECKARTAILFINGEN</u> <i>DEX</i>	STATE OR FOREIGN COUNTRY <u>GERMANY</u>	COUNTRY OF CITIZENSHIP <u>GERMANY</u> ✓
	6	POST OFFICE ADDRESS	POST OFFICE ADDRESS <u>HOHENNEUFFENSTRASSE 30</u>	CITY <u>D-72666 NECKARTAILFINGEN</u>	STATE & ZIP CODE/COUNTRY <u>GERMANY</u>
<p>I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.</p>					
SIGNATURE OF INVENTOR 202			SIGNATURE OF INVENTOR 205		
<i>Gregory H.P.</i>			<i>Horst Schneider</i>		
DATE 10.09.2001			DATE 10.09.2001		
SIGNATURE OF INVENTOR 206					
<i>Jürgen Stehllig</i>					
DATE 10.09.2001					